

# SolFilmsProdukter AB

## LLumar Bilfilmer

## LLumar Automotive Window Film

Visuellt Ljusgenomsläpp %  
 Total Solenergiavvisning %  
 Total Soltransmission %  
 Total Solreflektion %  
 Total Solabsorption %  
 Visuellt Ljusreflektion utv. %  
 UV-ljus genomsläpp %  
 Tjocklek utan skyddsfolie mm  
 Garantiid

ComfortSerien	High Performance Metallized film									10 år
ATRO5CHSRHPR	Mkt mörk Titanium	5	70	6	30	56	12	<1	0,045	
ATR5SDLRHPR	Alu Dark	5	70	14	30	56	12	<1	0,061	
ATR15CHSRHPR	Mörk Titanium	18	53	39	7	54	5	<1	0,044	
ATR20CHSRHPR	Mellan Titanium	21	48	28	18	54	8	<1	0,044	
ATR35CHSRHPR	Mellanljus Titanium	38	44	36	19	45	8	<1	0,044	
ATR50CHSRHPR	Visuell Titanium	55	34	59	8	33	8	<1	0,044	
AvantgardeSerien	NANO-Ceramic films (stör ej elektroniska signaler)									12 år
LATI05LSSRHPR	Ceramic Svart	5	61	21	6	74	8	<1	0,045	
LATI15LSSRHPR	Ceramic Mörk	18	57	22	5	73	6	<1	0,045	
LATI35LSSRHPR	Ceramic Mediumljus	38	51	31	6	63	6	<1	0,045	
LATI50LSSRHPR	Ceramic Light	55	46	38	6	56	7	<1	0,045	
EspritSerien	Premium dyed films (stör ej elektroniska signaler)									7 år
ATC05CHSRHPR	Mkt mörk Charcoal	5	44	41	6	53	8	<1	0,043	
ATC15CHSRHPR	Mörk Charcoal	20	39	48	6	46	8	<1	0,043	
ATC35CHSRHPR	Mellanljus Charcoal	37	33	56	5	39	8	<1	0,043	
ATC50CHSRHPR	Ljus Charcoal	54	29	63	7	30	8	<1	0,043	
ClassicSerien	Dyed films (stör ej elektroniska signaler)									5 år
AT05CHSRHPR	Mkt mörk Charcoal	5	46	39	7	54	5	<1	0,033	
AT20CHSRHPR	Mörk Charcoal	22	37	51	7	42	8	<1	0,031	
AT35CHSRHPR	Mellanljus Charcoal	37	32	58	7	35	8	<1	0,031	
AT50CHSRHPR	Ljus Charcoal	52	29	62	7	31	8	<1	0,031	
AT05GRSRHPR	Mkt mörk Grå	6	44	39	7	54	8	<1	0,031	
AT15GRSRHPR	Mörkt Grå	15	40	54	7	39	8	<1	0,03	
AT35GRSRHPR	Mellanljus Grå	38	32	58	7	35	8	<1	0,03	
AT50GRSRHPR	Ljus Grå	53	26	66	7	27	8	<1	0,03	
Specialfilmer										
XAP60GNSRPS	Climate Control	57	44	48	22	30	14	<1	0,045	
XAN03BKS RPS	Black Mirror	3	65	19,5	21	60	21 (inv 5)	<1	0,047	
AU75UVSRHPR	UV-Shield	78	21	74	9	17	9	<0,01	0,034	
AT35GNSRHPR	Classic Green	35	35	53	8	39	7	<1	0,031	
DL05BLSRPS	Metallic blå	7	76	10	32	58	20	<1	0,046	
DL25BLSRPS	Blue Titanium	32	51	35	13	52	10	<1	0,045	
SCLSRPS4	Säkerhetsfilm	89	16	81	9	10	8	<5	0,117	
SCLSRPS7	Säkerhetsfilm Thatcham accrediterad	88	16	81	9	10	8	<5	0,193	
AIR80BLSRHPR	IR-film	78	43	42	7	51	8	<1	0,046	
AIR75SRHPR	IR-film	74	41	49	7	44	9	<1	0,045	

\*Alla värden är vägledande riktvärden för film monterat på 3 mm glas.