

12 mil KLAR

Tekniskt Datablad

Tjocklek	12 mil
Tensile Strength at Break	28,500 PSI
Break Strength	336 lb/inch
Elongation at Break	125 %
Peel Strength	7 lb/inch

Specifikation

3 mm glas

Visuell Ljustransmission	87%
Visuell Ljusreflektion (Invändig)	11%
Visuell Ljusreflektion (Utvändig)	11%
UV-Ljusblockering	99%
Total Solenergreflektion	10%
Totalt Solenergitransmission	78%
Total Solenergiabsorption	12%
Bländningsskydd	3%
Skuggningskoefficient	0.94
G-Värde	0.82
U-Värde (USA)	1.07
U-Värde (EU c:a 2,8))	
Total Solenergiavvisning	18%

R32303T PS

SAFETY ACCREDITATIONS

Impact	EN 356 P2A	✓
	DIN 52290 Part 4, A1	✓
	ASTM E330	✓
Wind Debris	TAS 201, 202, 203 Florida Building Code (Dade County Small Missile Test) Hurricane	✓
	Siach Gefen IDF testing	✓x2 + No-Bar
Bomb Blast	UL 972 Burglary Resisting Glazing Material	✓
	GSA Level D (10.2 psi, 90.6 psi/msec)	✓(3A) x2 + No-Bar on both sides

EG-E DS No 1261, March 2012