

R 50 SR HPR LJUS SILVER

Teknisk Dataspecifikation

	Enkelglas	Tvåglas-isoler
	4 mm	4/16/4 mm
Total soltransmission	39 %	34 %
Total solreflektion	27 %	27 %
Total solabsorption	34 %	39 %
Visuell ljustransmission	49 %	45 %
Visuell ljusreflektion – Utvändig	24 %	29 %
Visuell ljusreflektion – Invändig	26 %	26 %
UV-ljusgenomsläpp	<1 %	<1 %
Skuggningskoefficient	0,58	0,68
Emissivitet	0,76	0,76
U-värde (EN 673 W/m ² k)	5,53	2,67
Bländningsskydd	45 %	45 %
G-värde (koefficient av total energitransmission)	0,47	0,54
Total solenergiavvisning	53 %	46 %
Tjocklek utan skyddsfolie/liner	45 μ	45 μ

Användningsområde och fördelar

- Reflekterar bort värme.
- Ger insynsskydd dagtid.
- Går att montera på insidan av 3-glas isoler.
OBS! Speciella begränsningar gäller
- Tar bort över 99% av UV-strålarna, skyddar mot blekning.
- LLumarfilm har ett patenterat repskydd.
- Finns även för utvändig montering: RHE 50 SI ER HPR.

Tillgängliga Bredder

✗	121,9 cm
✓	152,4 cm
✗	182,9 cm

LLumar Garanti

7 år på vertikalt glas

Film på glas rekommendation

✓	Klart Enkelglas	✓	Tonat enkelglas
✓	Klart 2-glas isoler	✓	Tonat 2-glas isoler
✓	Härdat/tonat enkelglas	✓	3 glas isoler

Alla värden och rekommendationer för film och glas är indikativa riktlinjer. Kontrollera alltid kompatibiliteten på förekommande glas noggrant innan installation. Kontakta SolFilmsProdukter AB för att erhålla korrekt specifikation för garanti mot termisk sprickbildning. Alla värden för LLumar fönsterfilm har uppmätts och beräknats i enlighet med EN410 metoden för glas och dess prestanda i förhållande till solens egenskaper på klart enkelt 4mm floatglas samt klart 2 glas isoler 4 + 4 mm. Alla värden har uppmätts från typiskt produktionsmaterial och är inom tillverkarens normala toleransnivåer. Verkliga prestanda beror på olika faktorer däribland glasets specifika konstruktion. Vi reserverar oss för eventuella feltryck.

© 2016 Eastman Chemical Company. LLumar® and the LLumar® logo are trademarks of Eastman Chemical Company or one of its wholly owned subsidiaries. The ® used herein denotes registered trademark status in the US; marks referenced herein may also be registered internationally. Visual renderings are for illustrative purposes only; actual appearance may vary. Although the information and recommendations set forth herein (hereafter "Information") are presented in good faith and believed to be correct as of the date hereof, neither Eastman Chemical Company nor any of its subsidiaries or affiliates (collectively, "Eastman") makes any representations or warranties as to the completeness or accuracy thereof and assumes no obligation to update any of the Information. Information is supplied upon the condition that the persons receiving same will make their own determinations as to its suitability for their purposes prior to use. In no event will Eastman be held responsible for damages or liability of any nature whatsoever, including without limitation, for direct, indirect or consequential loss, business interruption, loss of profits, production, goodwill or contracts, or anticipated savings, resulting from the use of or reliance upon the Information or the product to which the Information refers. No representations or warranties, either express or implied, of merchantability, fitness for a particular purpose, or of any other nature are made hereunder with respect to information or the product to which information refers.